



(11)

EP 0 964 009 A1

(12)

EUROPEAN PATENT APPLICATION

(43)

Date of publication:
15.12.1999 Bulletin 1999/50

(51)

Int Cl.⁶: C08F 214/22, C08F 214/26,
C08F 14/18

(21)

Application number: 99304195.3

(22)

Date of filing: 28.05.1999

<div>(84)</div> <div>Designated Contracting States: AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU MC NL PT SE Designated Extension States: AL LT LV MK RO SI</div> <div>(30)</div> <div>Priority: 08.06.1998 US 93320</div> <div>(71)</div> <div>Applicant: E.I. DU PONT DE NEMOURS AND COMPANY Wilmington Delaware 19898 (US)</div>	<div>(72)</div> <div>Inventor: Brothers, Paul Douglas Chadds Ford, Pennsylvania 19317 (US)</div> <div>(74)</div> <div>Representative: Matthews, Derek Peter Frank B. Dehn & Co., European Patent Attorneys, 179 Queen Victoria Street London EC4V 4EL (GB)</div>
---	--

(54)

Polymerization of fluoromonomers in carbon dioxide

(57)

Polymerization of vinylidene fluoride in carbon dioxide media is effectively initiated by dialkyl(2,2-azobisisobutyrate). Methyl is a preferred alkyl.

EP 0 964 009 A1

Description

FIELD OF THE INVENTION

[0001] This invention is in the field of processes for polymerizing fluoromonomers. Fluoromonomers for which the process is suitable include vinylidene fluoride and tetrafluoroethylene.

BACKGROUND OF THE INVENTION

[0002] The polymerization of vinylidene fluoride (VF_2) in aqueous media is well known. See, for example, Kirk-Othmer, "Encyclopedia of Chemical Technology" 4th ed., vol. 11, page 694 (1994), which mentions persulfate salts and disuccinic acid peroxide among water soluble initiators that can be used and dialkylperoxydicarbonate among monomer soluble initiators that can be used. Polymerization of VF_2 was first disclosed by Ford & Hanford in U.S. Patent 2,435,537 using initiators such as benzoyl peroxide and ammonium persulfate. Subsequently, Hauptschein in U.S. Patent 3,193,539 exemplified azo initiators, showing very low yield with azobisisobutyronitrile (AIBN), and Iserson in U.S. Patent 3,245,971 found AIBN to be ineffective.

[0003] The polymerization of certain fluorinated monomers in liquid or supercritical carbon dioxide is disclosed, for example, in Japanese Patent Application Publications 45-003390 (1970, Fukui *et al.*) and 06-345824 (1994, Ezaki *et al.*), Japanese Patent Publication 46-015511 (1971, Ukihashi *et al.*), and U.S. Patents 5,496,901 (DeSimone) and 5,618,894 (DeSimone & Romack). These references disclose various means of initiating polymerization including the use of ionizing radiation and assorted free radical initiators. The '901 patent discloses an extensive list of initiators that can be used including several azo compounds, and states a preference for azobisisobutyronitrile (AIBN).

[0004] As shown by tests summarized below, azo compounds commonly used to initiate polymerization are found not to work well, if at all, in attempted polymerizations of VF_2 in carbon dioxide. Notably, AIBN yields only a small amount of polymer.

[0005] However, azo initiators are desirable because of their predictable kinetics. As discussed by Sheppard & Kamath in Polymer Engineering and Science 19, 597 (1979), azo initiators do not undergo radical induced decomposition, and their decomposition rates are not affected by environment. Thus, it would be desirable to have an effective azo initiator for use in polymerizing VF_2 in carbon dioxide.

SUMMARY OF THE INVENTION

[0006] This invention provides a process for preparing a fluoropolymer, comprising polymerizing at least one fluorinated monomer in a fluid medium using an azo initiator, wherein said fluid medium comprises carbon di-

oxide, and said initiator is dialkyl(2,2'-azobisisobutyrate). Dimethyl(2,2'-azobisisobutyrate) is a preferred initiator.

[0007] This azo initiator is particularly effective for polymerizing vinylidene fluoride, and provides improved polymerization of tetrafluoroethylene.

DETAILED DESCRIPTION

10 [0008] It has been discovered that dialkyl(2,2'-azobisisobutyrate) is effective in initiating polymerization of vinylidene fluoride (VF_2) in media comprising carbon dioxide (CO_2), producing high molecular weight polymer at high yields. Additionally, this compound is especially
15 effective among azo compounds in initiating polymerization of tetrafluoroethylene (TFE).

[0009] The process of the present invention is generally similar to other processes for polymerizing fluorinated monomers in media comprising CO_2 , except for the
20 choice of specific azo initiator. While the examples below are carried out in batch mode, one skilled in the art will recognize that other modes of polymerization can be used, including semi-batch polymerization in which ingredients are added during polymerization, semi-continuous polymerization in which product is withdrawn
25 intermittently while ingredients are added either continuously or intermittently, and continuous polymerization in which product is withdrawn continuously. Any workable temperature and pressure can be used in the process of the invention. Generally, temperature is in the range
30 of 40°-125°C, preferably 60°-90°C, and pressure is in the range of 900-10,000 psig (6.3-69.1 MPa), preferably 1500-6000 psig (10.4-41.5 MPa).

[0010] The initiator used in the process of this invention is dialkyl(2,2'-azobisisobutyrate). Preferably, said
35 alkyl groups are independently selected from methyl, ethyl, propyl, n-butyl, isobutyl, secondary butyl, and n-amyl. More preferably, the alkyl groups are the same. Preferred alkyl groups include methyl and ethyl. Methyl is an especially preferred alkyl group. Ethyl is another
40 especially preferred alkyl group. Usually the amount of initiator used will be in the range of 0.001-25 mg/g of polymer produced, more commonly in the range of 0.005-10 mg/g of polymer produced.

45 [0011] The invention is useful for the manufacture of a wide variety of fluoropolymers. "Fluoropolymer" as used in this application is intended to encompass a broad spectrum of thermoplastic and elastomeric polymers of at least one fluorinated monomer. These fluoropolymers may be homopolymers of a fluoromonomer,
50 may be copolymers of two or more fluoromonomers, or may be copolymers of at least one fluoromonomer and at least one fluorine-free monomer. Generally, such fluoropolymers contain at least 35 wt% of fluorine.

55 [0012] "Fluoromonomer" is used in this application to mean a compound containing a vinyl group that may be free-radically polymerized and that contains at least one fluorine atom, fluoroalkyl group, or fluoroalkoxy group

attached to the vinyl group that undergoes polymerization. Preferred fluoromonomers are fluoroolefins. While the process of the present invention is particularly valuable for polymerizing VF₂ and TFE, useful fluoromonomers include, but are not limited to, vinyl fluoride; trifluoroethylene; chlorotrifluoroethylene (CTFE); 1,2-difluoroethylene; tetrafluoroethylene (TFE); hexafluoropropylene (HFP); perfluoro(alkyl vinyl ethers) such as perfluoro(methyl vinyl ether) (PMVE), perfluoro(ethyl vinyl ether) (PEVE), and perfluoro(propyl vinyl ether) (PPVE); perfluoro(1,3-dioxole); perfluoro(2,2-dimethyl-1,3-dioxole) (PDD); CF₂=CFOCF₂CF(CF₃)OCF₂CF₂X wherein X is SO₂F, CO₂H, CH₂OH, CH₂OCN or CH₂OPO₃H; CF₂=CFOCF₂CF₂SO₂F; F(CF₂)_nCH₂OCF=CF₂ wherein n is 1, 2, 3, 4 or 5; R¹CH₂OCF=CF₂ wherein R¹ is hydrogen or F(CF₂)_m and m is 1, 2 or 3; and R³OCF=CH₂ wherein R³ is F(CF₂)_z and z is 1, 2, 3 or 4; perfluorobutyl ethylene (PFBE); 3,3,3-trifluoropropene and 2-trifluoromethyl-3,3,3-trifluoro-1-propene. Preferred fluoromonomers are 3,3,3-trifluoropropene, 2-trifluoromethyl-3,3,3-trifluoro-1-propene, PFBE, vinyl fluoride, VF₂, HFP, PMVE, PEVE, PPVE, CTFE, and PDD.

[0013] The fluoromonomer may be polymerized alone to form a homopolymer if the fluoromonomer can be homopolymerized, or may be polymerized with one or more other fluoromonomers or other monomers that are not fluoromonomers to form a copolymer. If a copolymer is to be formed, the monomers chosen must be able to copolymerize. In copolymers, the other monomers preferably are fluorinated monomers and, more preferably, are fluoroolefins having 2-8 carbon atoms or fluorinated vinyl ethers having 3-8 carbon atoms. Especially preferred comonomers are tetrafluoroethylene, hexafluoropropylene, perfluoro(methyl vinyl ether), perfluoro(ethyl vinyl ether), and perfluoro(propyl vinyl ether). Fluorine-free monomers that copolymerize with some combinations of fluoromonomers include propylene and ethylene. Examples of useful homopolymer fluoropolymers include polyvinylidene fluoride (PVF₂) and polytetrafluoroethylene (PTFE). Also usually classed with homopolymer PTFE are the modified PTFE polymers containing fluoromonomers other than TFE in such minor amounts that the modified polymers retain the non-melt-fabricable character of PTFE. Examples of useful copolymers include the copolymers of TFE with HFP and/or perfluorinated vinyl ethers such as PPVE or PEVE, copolymers of TFE with PMVE, copolymers of TFE with PDD, and copolymers of TFE or CTFE with ethylene. Further examples include the copolymers of VF₂ with HFP, or with HFP and TFE. As implied above, copolymers may contain additional monomers beyond those named. TFE/ethylene copolymers, for example, are most useful if they include additional monomers that introduce bulky side groups such as PFBE, HFP, PPVE or 2-trifluoromethyl-3,3,3-trifluoro-1-propene, and elastomeric polymers frequently include low concentrations of cure site moieties derived from a cure site monomer

and/or a chain transfer agent (CTA).

EXAMPLES

- 5 [0014] The normal practice in charging gaseous constituents to a shaker tube for polymerization reactions such as described below is to charge the gases in a sequence determined by the source pressures, starting with the low-pressure gas and proceeding to the high-pressure gas. It is common to charge CO₂ first, because cylinder pressures for CO₂ are usually low. When TFE is used, it is charged as a mixture with CO₂, usually 50/50 by weight, and supplemental CO₂ is charged separately to arrive at the stated CO₂ charge.
- 10 [0015] Copolymer compositions are determined by ¹⁹F NMR spectroscopy, which is also used to confirm the structure of polyvinylidene fluoride. Fourier transform infrared spectroscopy (FTIR) is used to confirm the structure of PTFE.
- 15 [0016] Thermal characteristics of polymers are determined by differential scanning calorimetry (DSC) according to ASTM D-4591. Unless otherwise stated, melting temperature (T_m) and heat of fusion (ΔH_f) are derived from the melting endotherm on second heating, with melting temperature being the peak temperature.
- 20 [0017] Melt flow rate (MFR) of fluoropolymers is determined according to ASTM method D-1238-94a, using a plastometer modified by use of corrosion-resistant alloy as described in ASTM specification D-2116-91a, and using a 5 kg load at temperatures of 232°C for all VF₂ polymers and 372°C for PTFE. Melt flow is zero in several of the examples to follow, indicating high molecular weight. While this is expected and desirable for PTFE, except for PTFE micropowder, such high molecular weight is incompatible with conventional melt processing of other polymers. One skilled in the art will recognize that molecular weight can be regulated to achieve melt viscosity in commercially desirable ranges for melt-flowable polymers, e.g., from 50 Pa·s to 1 × 10⁵ Pa·s, preferably from 500 Pa·s to 5 × 10⁴ Pa·s, by adjusting initiator concentration, by the use of chain transfer agents, and the like.
- 25 30 35 40 45

Comparison A

- 45 [0018] A 400 mL stainless steel vessel (shaker tube) is thoroughly cleaned and cooled to approximately 0°C. The vessel is flushed with nitrogen to remove all oxygen and 0.09 g of 2,2'-azobis(2,4-dimethylpentanenitrile) (VAZO® 52, DuPont) is quickly added to the vessel. Then the vessel is sealed, evacuated, and cooled to less than -40°C. Through an addition port equipped with a high pressure block valve, 100 g of vinylidene fluoride (VF₂) and 225 g of CO₂ (99.99% pure with less than 9 ppm of O₂, Coleman Grade, M-G Industries) are then added and the block valve is closed. While agitating, the vessel is heated to increase the temperature of the contents to 55°C, at which point the autogenous pressure
- 50 55

is about 4100 psig (28.4 MPa). After 10 hr, the vessel is cooled, pressure is released and the vessel is opened. No polymer is produced.

Comparison B

[0019] The procedure of Comparison A is essentially repeated, except that 0.06 g of 2,2'-azobis(2-methylpropanenitrile) (VAZO® 64, DuPont, also called azobisisobutyronitrile or AIBN) is used instead of the VAZO® 52, the temperature is 68°C, and the resultant autogenous pressure is about 5100 psig (35.3 MPa). The initiator amount and temperature are set to produce the same number of radicals over a 10 hr period as produced in Comparison A. After 10 hr, the autogenous pressure has dropped to about 5000 psig (34.6 MPa), the vessel is cooled, pressure is released and the vessel is opened. Only 2.6 g of white polymer are recovered. The polymer is confirmed by ¹⁹F NMR in acetone at room temperature to be polyvinylidene fluoride having 4.3 mol% of head-to-head units, and has $T_m = 169^\circ\text{C}$ and $\Delta H_f = 62 \text{ J/g}$.

Example 1

[0020] The procedure of Comparison A is essentially repeated, except that 0.082 g of dimethyl(2,2'-azobisisobutyrate) (V-601, Wako Pure Chemical Industries, Ltd.) is used instead of the VAZO® 52, the temperature is 69.5°C, and the resultant autogenous pressure is approximately 5000 psig (34.6 MPa). The initiator amount and temperature are set to produce the same number of radicals over a 10 hr period as produced in Comparisons A and B. After 10 hr, the autogenous pressure has dropped to about 4400 psig (30.4 MPa), the vessel is cooled, pressure is released and the vessel is opened. The amount of polymer recovered as a white powder is 22.8 g, showing the effectiveness of dialkyl(2,2'-azobisisobutyrate) in contrast to other azo initiators. The polymer is confirmed by ¹⁹F NMR in DMAC at 100°C to be polyvinylidene fluoride having 4.6 mol% of head-to-head units. T_m is 169°C, ΔH_f is 58 J/g, and MFR is 0 g/10 min. The plug removed from the melt flow apparatus is loosely fused and off-white in color.

Comparison C

[0021] The procedure of Comparison A is essentially repeated, except that 0.10 g of 2,2'-azobis(N,N'-dimethyleneisobutyramidine)dihydrochloride (VA-044, Wako) is used instead of the VAZO® 52, the amount of CO₂ is 275 g, 50 g of TFE are used instead of VF₂, the temperature is 55°C, and the run time is 4 hr. The resultant autogenous pressure is about 3250 psig (22.5 MPa) and is nearly constant throughout the run. Only 0.04 g of product is recovered, which thermogravimetric analysis suggests is low-molecular-weight PTFE.

Comparison D

[0022] The procedure of Comparison C is essentially repeated except that 0.06 g of AIBN is used instead of the VA-044, the temperature is 68°C, the autogenous pressure is 4600 psig (31.8 MPa), and the run time is 10 hr. At the end of the run, the pressure is 4000 psig (27.7 MPa). The amount of polymer recovered as a white powder is 33.1 g. T_m is 330°C and ΔH_f is 72 J/g. FTIR confirms that the polymer is PTFE. MFR is 0 g/10 min.

Example 2

[0023] The procedure of Comparison D is essentially repeated except that 0.082 g of V-601 is used instead of AIBN, and the temperature increases to 160°C due to the exothermic reaction before returning to 68°C. At the end of the run, the pressure is 3000 psig (20.8 MPa). The amount of polymer ($T_m = 331^\circ\text{C}$ and $\Delta H_f = 71 \text{ J/g}$) recovered as a white powder is 45.2 g (90.4% yield), showing the effectiveness of dialkyl(2,2'-azobisisobutyrate) in polymerizing TFE. FTIR confirms that the polymer is PTFE and MFR is 0 g/10 min, indicating high molecular weight. The plug removed from the melt flow apparatus is fused and white in color.

Examples 3-6

[0024] The procedure of Example 1 is essentially repeated except that mixtures of VF₂ and TFE monomers are used instead of VF₂ alone, and the reaction time is 5 hr, except for Example 4 for which the reaction time is 1.5 hr. Monomer charges, yields of partially-crystalline polymers, and melting temperatures (T_m) of the product copolymers are shown in Table 1. The results indicate that dialkyl(2,2'-azobisisobutyrate) is effective for initiating polymerization of VF₂/TFE copolymers. MFR is measured at 232°C. For Examples 5 and 6, the resin plugs in the MFR apparatus are loosely fused, a further indication of very high molecular weight, and are white in color. For Examples 3 and 4, the resin plugs in the MFR apparatus are fused and off-white.

Table 1.

Conditions and Results for Examples 3-6				
	3	4	5	6
Conditions:				
VF ₂ charge (g)	23.0	50.0	64.0	80.5
TFE charge (g)	50.0	46.5	34.8	19.5
Results:				
Yield (g)	53.8	34.9	59.1	35.5
(%)	73.6	36.1	59.7	35.4
T_m (°C)	205	173	145	130

Table 1. (continued)

Conditions and Results for Examples 3-6				
Results:				
MFR (g/10 min)	0	0	0	0
VF ₂ (wt%)	---	41.0	---	78.6
TFE (wt%)	---	59.0	---	21.4

Examples 7-10

[0025] The procedure of Example 1 is essentially repeated except that mixtures of VF₂ and hexafluoropropylene (HFP) monomers are used instead of VF₂ alone, and the CO₂ charge is varied as shown in Table 2. Monomer charges, test pressures (p), and polymer yields are also shown in Table 2. The results indicate that dialkyl(2,2-azobisisobutyrate) is effective for initiating polymerization of VF₂/HFP copolymers.

Table 2.

Conditions and Results for Examples 7-10				
	7	8	9	10
Conditions:				
CO ₂ charge (g)	225	175	175	175
VF ₂ charge (g)	65	117	106	95
HFP charge (g)	5	78	44	55
Initial p (MPa)	35.3	41.1	29.3	24.2
Final p (MPa)	27.0	30.1	23.1	19.1
Results:				
Yield (g)	39.2	47.5	35.0	18.7
(%)	55.9	24.3	23.3	12.4
T _m (°C)	163	118	135	128
ΔH _f (J/g)	54	26	33	31
MFR (g/10 min)	0	0	0	0.6
VF ₂ (wt%)	98.2	85.3	89.4	86.3
HFP (wt%)	1.8	14.7	10.6	13.7

Example 11

[0026] The procedure of Example 1 is essentially repeated except that vinyl fluoride is used instead of vinylidene fluoride. At the end of the run, the pressure is 3100 psig (21.5 MPa). The amount of polymer recovered as a white powder is 61.7 g, showing the effectiveness of dialkyl(2,2-azobisisobutyrate) in polymerizing vinyl fluoride. NMR confirms that the product is polyvinyl fluoride having 2.1 mol% of tertiary fluorine (normal branching) and 12.3 mol% of linear head-to-head units. T_m is 186°C and ΔH_f is 43 J/g. A relative measure of molecular weight is obtained by capillary rheometry on a mixture of 40 wt% polymer in dimethylacetamide with the rheometer operated at 150°C. Viscosities are measured at shear rates ranging from 23.4 sec⁻¹ to 3516

sec⁻¹. A logarithmic plot of these data is fit to a linear least squares equation which is then used to calculate the viscosity at 100 sec⁻¹. The melt viscosity so obtained is 266 Pa·s.

Claims

1. A process for preparing a fluoropolymer, comprising polymerizing at least one fluorinated monomer in a fluid medium using an azo initiator, wherein said fluid medium comprises carbon dioxide, said initiator is dialkyl(2,2'-azobisisobutyrate).
2. The process of Claim 1, wherein said monomer is fluoroolefin.
3. The process of Claim 1, wherein said polymer is a copolymer of fluoroolefin and at least one copolymerizable fluorinated comonomer.
4. The process of Claim 3, wherein said comonomer is selected from fluoroolefins, other than said fluoroolefin, having 2-8 carbon atoms and fluorinated vinyl ethers having 3-8 carbon atoms.
5. The process of Claim 2, wherein said fluoroolefin is vinylidene fluoride or tetrafluoroethylene.
6. The process of Claim 4, wherein said comonomer is at least one of tetrafluoroethylene, hexafluoropropylene, perfluoro(methyl vinyl ether), perfluoro(ethyl vinyl ether), and perfluoro(propyl vinyl ether).
7. The process of Claim 3, wherein said polymer is elastomeric.
8. The process of Claim 3, wherein said polymer is thermoplastic.
9. The process of Claim 1, wherein said polymer is a homopolymer.
10. The process of Claim 1, wherein said carbon dioxide is liquid or supercritical.
11. The process of Claim 1, wherein said medium consists essentially of carbon dioxide.
12. The process of Claim 1, wherein said alkyls are independently selected from methyl, ethyl, propyl, n-butyl, isobutyl, secondary butyl, and n-amyl.
13. The process of Claim 1, wherein each of said alkyls is methyl.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 30 4195

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X,D	US 5 496 901 A (THE UNIVERSITY OF NORTH CAROLINA AT NORTH CHAPEL) 14 October 1993 (1993-10-14) * abstract; examples 1,28,30 *	1-13	C08F214/22 C08F214/26 C08F14/18
A	EP 0 779 335 A (DAIKIN IND LTD) 18 June 1997 (1997-06-18) * page 21, line 46; table 2 *	1-6	
A	EP 0 388 172 A (SHINETSU CHEMICAL CO) 19 September 1990 (1990-09-19) * page 3, line 20-25; claim 6; examples *	1-6	
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			C08F
The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
THE HAGUE		27 September 1999	Friederich, P
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/92 (P4/Col1)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 30 4195

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-09-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5496901 A	05-03-1996	US 5739223 A	14-04-1998
		US 5688879 A	18-11-1997
		US 5863612 A	26-01-1999
		AU 3776393 A	08-11-1993
		EP 0638095 A	15-02-1995
		JP 7505429 T	15-06-1995
		WO 9320116 A	14-10-1993
		US 5922833 A	13-07-1999
EP 0779335 A	18-06-1997	JP 8067795 A	12-03-1996
		US 5804650 A	08-09-1998
		WO 9606887 A	07-03-1996
EP 0388172 A	19-09-1990	JP 2240119 A	25-09-1990
		US 5109086 A	28-04-1992

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82